

**McIlvaine Hot Topic Hour**  
**Catalyst Selection for NO<sub>x</sub> and Other Gases**  
**November 29<sup>th</sup>, 2012**

**Enhanced Mercury Control  
by Managing SCR Systems  
for Mercury and NO<sub>x</sub>**

**Scott Hinton, Ph.D., P.E.**

**W.S. HINTON & ASSOCIATES**

**1612 Smugglers Cove Circle**

**Gulf Breeze, FL 32564**

**Tel: 850-936-0037**

**shinton@wshinton.com**



**W. S. Hinton & Assoc.**

# GENERAL PRECAUTIONS !

**SCR Focus:** The of the presentation is SCR mercury oxidation. However, many downstream factors will influence mercury speciation and capture. Avoid making the assumption that a speciation change at the SCR will have the same direct quantitative effect on mercury capture at the stack. The system must be treated in an integrated fashion.


**Use Data as Examples Only:** Much of the data presented are associated with pilot facilities. These data may not translate directly to full-scale systems, especially in terms of the absolute values for halogens and mercury oxidation. In other words, the scales may be shifted !

**Mercury Oxidation is Site Specific !** Data from one facility may not translate directly to another facility, even if facilities appear to be very similar.


# Factors Affecting SCR Mercury Oxidation

- **Fuel Composition** (mercury and halogen Levels)
- **Supplemental Halogens** (chlorine or bromine addition)
- **Catalyst Design** (pitch, formulation, etc.)
- **Volume/Potential**
- **Catalyst Age**
- **Temperature**
- **Flow Rate**
- **Ammonia**

# Fuel Composition – Mercury Levels




# Fuel Composition – Chlorine Levels




# Bromine and Chlorine Inter-Relationship

Coals low in Chlorine will also generally be low in Bromine




# Example Effect of Chlorine on SCR Hg Oxidation



# Bromine Addition with SCR-Wet Scrubber

MRC Data - low chlorine eastern bituminous coal




**Caution !** Example only –effects may be significantly shifted in the field.



# SCR Outlet Oxidized Mercury vs. Temperature


lower temperatures favor oxidized mercury



Based on MRC data  
4 catalysts


# Effect of Ammonia: Suppression of Hg Oxidation

halogens can help to mitigate the effect




**Caution !** Example only – halogen effects may be significantly shifted in the field.

# Effect of Ammonia: Speciation as a Function of Catalyst Layer



# Effect of Ammonia: Speciation as a Function of Catalyst Layers



# GENERAL OPERATING GUIDELINES TO MAXIMIZE MERCURY OXIDATION AND MINIMIZE EMISSIONS

- **Avoid High-Mercury in Fuel**
- **High Halogens**  
(through fuel purchasing, blending, or supplementation)
- **Lower Temperatures**
- **Lower Flow Rates/Low Space Velocity**
- **Minimize the Ammonia Profile**  
(through good SCR maintenance, AIG tuning, cleanliness, distributions, etc.)

# TWO CATALYST MANAGEMENT STRATEGIES TO IMPROVE MERCURY OXIDATION AND MAINTAIN DENOX

**Strategy A** – Aggressively Maximizes Mercury Oxidation

**Strategy B** – Modest Approach to Improve Mercury Oxidation

# Strategy A

- **Most Aggressive Strategy**
- **Manages Upper Catalyst Layers for DeNOx**
- **Manages Final Catalyst Layer for Mercury Oxidation**
- **Insures that Entire Final Catalyst Layer Operates with Very Low Slip (< 2 ppmv normally)**
- **Results in One Extra Layer Always Being Present in Reactor**
- **Fine Tuning Parameters: Frequency of Final Layer Replacement, Use of Advanced Catalyst, Allowable Slip Entering Final Layer, Halogen Injection Level (if used)**
- **Costs:** Full Layer of Additional Catalyst, Pressure Drop, Maintenance, Sootblowing/Horn Provisions, More Frequent Management Events

# STRATEGY A – Manages Reactor in Two Parts

## 4-Layer Reactor Design

<b>Layer 1</b> High deNOx – Very Limited Hg Oxidation
<b>Layer 2</b> Moderate deNOx – Limited Hg Oxidation
<b>Layer 3</b> Low deNOx – Moderate Hg Oxidation
<i>NH<sub>3</sub> Slip = 2-5 ppmv</i>
<b>Layer 4</b> ~No deNOx – High Hg Oxidation
<i>NH<sub>3</sub> slip ≈ 0, Hg Oxid. ≈ 90%+</i>

## 3-Layer Reactor Design

<b>Layer 1</b> High deNOx – Very Limited Hg Oxidation
<b>Layer 2</b> Moderate/Low deNOx - Limited Hg Oxidation
<i>NH<sub>3</sub> Slip = 2-5 ppmv</i>
<b>Layer 3</b> ~No deNOx – High Hg Oxidation
<i>NH<sub>3</sub> slip ≈ 0, Hg Oxid. ≈ 90%+</i>


### Key

DeNOx Layers

Mercury Oxidation Layers




# STRATEGY A – CATALYST MANAGEMENT PLAN




# Strategy B

- **Moderate Strategy to Improve Mercury Oxidation**
- **Manages Reactor as a Whole, Following Typical Management Strategy in General Approach**
- **Relies on “Excess Potential” to Insure that Some Portion of Catalyst Operates at Very Low Slip Over the Life of the Installation.**
- **Results in More Frequent Catalyst Replacements, or Requires More Potential Per Layer (via deeper beds, tighter pitch, or possibly more active catalyst)**
- **Caution: Do Not Allow Excess Potential to be an Excuse for Sloppy Operation and Maintenance of the SCR System**
- **Fine Tuning Parameters: Required Excess Potential, Use of Advanced Catalyst, Halogen Injection Level (if used)**
- **Costs:** additional catalyst, more frequent management events

# Strategy B – Catalyst Management Plan



# Management Strategy Selection: Decision Tree



# SUMMARY - CATALYST MANAGEMENT STRATEGIES FOR MERCURY CONTROL

Strategy	A	B
Aggressiveness	High	Moderate
General Application	Facilities that have very limited mercury oxidation under normal operation	Facilities that routinely achieve, or nearly achieve, the required mercury removal under normal operation
Halogen Level	Often low native halogen coals (PRB and domestic/foreign low-chlorine coals), with halogen supplementation required/other facilities for which demand for SCR mercury oxidation is high	Usually moderate to high-halogen coals where no halogen supplementation is required/ other facilities for which demand for SCR mercury oxidation is low or moderate
Approach	Manage final catalyst layer as a mercury oxidation catalyst with very low ammonia – upper catalyst layers managed for deNOx	Manage entire reactor as a whole using excess reactor potential to insure adequate mercury oxidation
Variables (fine tuning parameters)	<ol style="list-style-type: none"> <li>1) Allowable slip entering the final catalyst layer</li> <li>2) Allowable deactivation of final layer prior to replacement</li> <li>3) Halogen and/or sorbent injection rate, if utilized</li> <li>4) Use of Advanced Catalyst</li> </ol>	<ol style="list-style-type: none"> <li>1) Amount of excess potential required to meet the desired margin in mercury removal</li> <li>2) Halogen and/or sorbent injection rate, if utilized</li> <li>3) Use of Advanced Catalyst</li> </ol>

# Economic Considerations of Catalyst Management for Mercury Control

Category	Costs		Benefits
	Strategy A	Strategy B	
Fixed Capital	Cost of full catalyst layer, possibly cost of cleaning system and instrumentation for additional layer	Cost of additional catalyst potential	Possible avoidance of sorbent injection or halogen injection
Variable	Pressure drop associated with additional catalyst	Pressure drop associated with additional catalyst	Reduction in sorbent or halogen usage
Maintenance	General maintenance catalyst replacement events associated with final layer	More frequent catalyst replacement events	Possible benefit to downstream equipment due to lower ammonia slip

# DATA SHORTFALLS

- **Quantitative speciation benefit from the management strategies as a function of fuel and operating conditions.**
- **Direct quantitative effect on emissions due to SCR oxidation change, as a function of operating conditions.**
- **Advantages of advanced catalyst over conventional catalyst as a function of operating conditions, and location in reactor.**

# ADVANCED VERSUS CONVENTIONAL CATALYST

- Advanced catalyst is designed to offer higher mercury oxidation while maintaining deNO<sub>x</sub> and SO<sub>2</sub> conversion.
- Some price premium is expected.
- Both catalyst management plans can utilize advanced catalyst.
- Advanced catalyst probably most beneficial in last layer.
- Most aggressive strategy is to use Strategy A with advanced catalyst in entire reactor, or alternately only the last layer would use advanced catalyst.
- Currently the differential mercury oxidation between advanced catalyst and conventional catalyst is not known independently.
- Cost analyses will depend on the above and the price differential.





W. Scott Hinton, Ph.D., P.E.

***W.S. HINTON & ASSOCIATES***

1612 Smugglers Cove Circle

Gulf Breeze, FL 32563

Office: 850-936-0037

Cell: 850-261-5239

email: [shinton@wshinton.com](mailto:shinton@wshinton.com)